



# Highland International, Inc.

## Engineered Paint Systems

### HiTemp 802-HA Gray Hot Application 600°F Silicone Copolymer DTM/Topcoat

**HiTemp 802-HA** is a silicone alkyd high heat coating effective on steel surfaces up to 600°F. 802-HA has been modified so that it may be applied directly to hot surfaces up to 325°F.

<b>Vehicle Type:</b>	Silicone Alkyd
<b>Pigmentation:</b>	Black Iron Oxide & Titanium
<b>Reducer:</b>	#101 Hot Application Reducer 20%
<b>Mix Ratio:</b>	Single Package
<b>Pot Life:</b>	Not Applicable
<b>Volume Solids:</b>	51%
<b>Theoretical Coverage:</b>	816 ft <sup>2</sup> /gal. @ 1 Mil DFT
<b>Flash Point:</b>	16°F (Lowest Flashing Component)
<b>Recommended DFT:</b>	3-5 mils as a DTM 2-3 mils as a Topcoat

#### Dry-time:

<b>To Touch:</b>	N/A
<b>Tack Free:</b>	N/A
<b>To Recoat:</b>	Within 5-10 Minutes
<b>To Handle</b>	N/A
<b>Put in Service:</b>	Immediately

<b>VOC:</b>	3.49 lbs per gallon (417 grams/liter)
<b>Shelf Life:</b>	1 Year from DOM
<b>Finish:</b>	Eggshell
<b>Color:</b>	Gray
<b>Put in Service:</b>	12 Hours

#### Surface Preparation

- 1) All surfaces to be painted should be dry and free of all foreign contaminants.
- 2) 802-HA may be applied over existing coatings.
- 3) Minimum acceptable surface preparation should be in accordance with SSPC-SP6 Commercial Blast.
- 4) A low profile blast (1.5 to no more than 2 mils) is preferred.
- 5) Apply directly to steel in two coats to achieve proper DFT or apply over #830 or #860 HiTemp Primer for temperatures up to 400°F.

For extra durability and corrosion protection apply over #47 Chem-Temp Epoxy Hybrid for temperatures up to 500°F.

#### Mixing and Application Requirements

- 1) Stir product thoroughly prior to use
- 2) Apply at a rate of 204-272 square feet per gallon to obtain the recommended film thickness when using as a DTM.
- 3) Apply at a rate of 272-408 square feet per gallon to obtain the recommended film thickness when using as a topcoat.

**SPECIAL NOTES:** When using as a topcoat apply no more than 2-3 mils DFT. To prevent delamination and/or gas bubbles do not exceed a total dry film thickness of 5 mils when applying as a topcoat or DTM

#### Method of Application

<b>Conventional Gun:</b>	DeVilbiss MBC-510
Fluid Tip:	E
Air Cap:	704
Atomizing Pressure:	60 psi
Pot Pressure:	15-20 psi
Hose:	3/8 inch ID
<b>Airless Gun:</b>	Graco 205-591
Pump:	30:1/45:1/60/1, Gas Pump is Acceptable
Tip Range:	3.011 – 4.015
Pump Pressure:	1800 psi minimum
Hose:	3/8 inch ID
Brush or Roller:	Touch Up Only
Clean Up:	Clean all equipment lacquer thinner

#### Safety Precautions

- 1) Use normal precautions such as gloves, facemasks and barrier creams.
- 2) Adequate ventilation must be maintained. In confined areas, workmen must wear constant flow airline respirators.
- 3) If product comes into contact with skin, wash thoroughly with lukewarm water or diluted Boric Acid, and obtain immediate medical attention.
- 4) This product contains **FLAMMABLE** materials. Keep away from sparks and open flames. Observe **NO SMOKING** regulations.
- 5) All electrical equipment and installations should conform to NEC regulations. In areas where explosion hazards exist, workmen should be required to use non-ferrous tools, and to wear conductive, non sparking shoes.
- 6) Observe low flash regulations.
- 7) Refer to Material Safety Data Sheet (MSDS) for complete safety instructions.

The technical data listed herein has been compiled for your convenience and guidelines are based upon our experience and knowledge. However, since we have no control over the use of this information or this product, no warranty expressed or implied is intended or given. Highland assumes no responsibility whatsoever for coverage, performance or any other damage, including injuries from use of this information or products recommended herein.