

# 74-HF Series

## ChemTemp Hybrid Epoxy Novolac DTM/Liner



Chem-Temp 74-HF Series is a thin film 2-K Hybrid Epoxy Novolac DTM/ Liner Coating that offers exceptional temperature and chemical protection. Specifically formulated for tank linings, vessels, and pipelines, 74-HF Series provides superior barrier properties against acidic, caustic, and high heat environments. Chem-Temp 74-HF Series also offers excellent adhesion and corrosion resistance with a temperature rating of 300°F for immersion (350°F for some cargoes/services) and 450°F for dry heat or CUI services, making it the premium choice for high performance against corrosive cargo.

### Tech Specs

<b>Heat Resistance:</b>	350°F for immersion services 450°F for dry heat services
<b>Vehicle Type:</b>	Hybrid Epoxy Novolac
<b>Reducer:</b>	Not Normally Required
If desired:	#740S (slow) #740M (medium) #740F (Fast)
<b>Mix Ratio:</b>	4:1 Base:Activator
<b>Pot Life:</b>	3 Hours @ 77°F (Decreases in higher temperatures)
<b>Volume Solids:</b>	70%
<b>Theoretical Coverage:</b>	1122ft <sup>2</sup> /gal. @ 1 mil DFT
<b>VOC:</b>	<247 g/L
<b>Flash Point:</b>	24°F (Lowest Flashing Component)

<b>Dry Film Thickness:</b>	10-18 mils DFT in 2 coats
<b>Wet Film Thickness:</b>	8.6 – 12.9 mils WFT per coat
<b>Dry-time:</b>	<b>Normal</b>
To Touch:	4 Hours
To Recoat:	Minimum – 3 Hours Maximum – 36 Hours
Full Cure:	7 Days or 24 Hours after final coat when force cured
<b>Shelf Life:</b>	2 Years Minimum
<b>Finish:</b>	Eggshell
<b>Color:</b>	Standard and Custom
<b>Packaging:</b>	5 Gallon & 1 Gallon Kits
<b>Storage Temperature:</b>	20°F - 110°F

### Surface Preparation

All surfaces should be clean, dry and free of all foreign contaminants.

A SSPC-SP1 Solvent Cleaning with Highland 901 Cleaning Solvent is recommended before blasting or other cleaning method.

#### Carbon Steel - Immersion:

Obtain a 2-3 mil angular blast profile using one of the recommended methods below.

**Best:** A SSPC-SP5/NACE 1 White Metal Blast Cleaning is recommended for maximum coating performance and longevity.

**Good:** A SSPC-SP10/NACE 2 Near White Metal Blast Cleaning provides good results.

#### Carbon Steel - Non-Immersion:

Obtain a 2-3 mil angular blast profile using one of the recommended methods below.

**Best:** A SSPC-SP10/NACE 2 Near White Metal Blast Cleaning is recommended for maximum coating performance and longevity.

**Good:** A SSPC-SP6/NACE 3 Commercial Blast Cleaning provides good results.

#### Galvanized Steel:

Contact a Highland representative as recommendation will vary depending on substrate and exposure conditions.

Note: Allow one week at 77°F before being put into service (unless force cured). The second coat/topcoat must be applied within 36 hours at 77°F or the surface will need to be scuffed.

## Mixing & Application

**Mixing:** Highland 74-HF Series needs to be thoroughly mixed using mechanical agitation. Mix entire contents of Part "A" Activator with Part "B" Base (4:1 by volume) Product is ready to spray after proper mixing and a 30 minute induction period.

**Reduction:** Reduction is not required, if desired, reduce by 0% - 10% with Highland #740 reducer.

Highland 74-HF Series is designed for spray application. To ensure optimal performance, apply according to recommendations below.

**Airless Gun:** Graco 205-591  
**Pump:** 30:1/45:1/60:1  
**Tip Range:** 3.013 – 4.017  
**Pump Pressure:** 1,800 psi Minimum  
**Hose:** 3/8 inch ID

**Brush or Roller:** Both are acceptable for touch up.

**Conventional Gun:** DeVilbiss MBC-510  
**Fluid Tip:** E  
**Air Cap:** 704  
**Atomizing Pressure:** 70 psi  
**Pot Pressure:** 15-20 psi  
**Hose:** 1/2 inch

**Clean Up:** Highland #901 Cleaning Solvent

## Typical Systems

**Standard/Immersion Service:** Apply 8-18 mils DFT of 74-HF Series in 2 coats at 6-9 mils per coat directly to prepared steel.

Highland 74-HF Series may also be topcoated with a variety of Highland Topcoats. Contact your Highland representative for details.

## Advantages

- Next generation polymer technology specifically engineered for heat stability and chemical resistance
- Dry heat stability up to 450°F, immersion up to 300°F (350°F for some cargoes/services)
- Superior resistance to a wide variety of chemicals and solvents
- Superior abrasion resistance
- Superior adhesion even over marginally prepared surfaces
- Excellent corrosion resistance
- Ease of application
- Specially engineered inert filler package provides superior barrier properties
- Superior substrate wetting provides excellent adhesion and corrosion protection
- Ultra-high crosslink density provides a tough durable film with long lasting protection

## Performance Data

**Adhesion** > 1800 psi  
(ASTM D 4541) – Commercial Blast

**Abrasion Resistance** Excellent – 124 mg loss  
(ASTM D 4060) 1000 Cycles, 1000g load

**Humidity Resistance** Excellent – No blistering or other defects observed  
(ASTM 4585) 3000 hours

**Salt Spray Resistance** Excellent - <1 mm creep from scribe, no blistering  
(ASTM B 117) 3000 hours

**Chemical Resistance** Excellent – MEK – No defects observed  
(ASTM D 1308) 25% H2SO4 – Slight discoloration, no other defects observed  
25% NaOH – slight loss of gloss, no other defects observed

**Pencil Hardness** 6H  
(ASTM D 3363)

**Elongation** 5%  
(ASTM D 522)

### RAE Engineering and Inspection Ltd. May 2011

NACE TM0185 – Evaluation of Internal Plastic Coatings for Corrosion Control of Tubular Goods by Autoclave Testing.

#### Adhesion

**Method:** ASTM D4541 – Standard Test Method for Pull-Off Strength

**System:** Two coats 74 Series @ 8 mils DFT per coat applied to:  
1) SSPC-SP6 Commercial Blast prepared steel  
2) No surface preparation

**Result:** 1) No less than 1400 psi with SSPC-SP6 Commercial Blast  
2) No less than 1000 psi with no surface preparation.

#### Chemical Immersion

**Method:** Continuous Immersion at 93°C (200°F)

**System:** Two coats 74 Series @ 8 mils DFT per coat applied to SSPC-SP5 White Metal Blast prepared steel. Cured 14 days at 21°C (70°F).

**Result:** No cracking, lifting, or delamination after 60 days of continuous exposure.

**Reagents:** 10% methanol, 50% methanol, 10% sulfuric acid, 25% sulfuric acid, 10% sodium hydroxide, 50% Sodium hydroxide.

#### Heat Resistance

**Method:** Continuous heat exposure at 232°C (450°F)

**System:** Two coats 74 Series @ 8 mils DFT per coat applied to:  
1) SSPC-SP56 Commercial Blast prepared steel  
2) No surface preparation  
3) No surface preparation with tight rust.  
Cured 14 days at 21°C (70°F).

**Result:** No cracking, lifting, or delamination of the film after 3000 hours of continuous exposure.

#### Acid Condensation Bath

**Method:** Coated panels exposed to a condensation bath with 50% sulfuric acid and water. The test duration was 1000 hours total at 177°C (350°F) and the panels were scribed with an "X" to evaluate corrosion. The acid bath was performed in an enclosed apparatus that retained the sulfuric acid condensation, and the panels were suspended in the headspace.

**System:** Single coat as well as two coats 74 Series @ 8 mils DFT per coat applied to SSPC-SP6 Commercial Blast prepared steel. Cured 24 hours at 21°C (70°F).

**Result:** No rust creepage, softening, cracking or delamination of the film after 1000 hours of continuous exposure.

#### Sulfuric Acid Spot Testing

**Method:** Continuous heat at 177°C (350°F) for 1500 hours. After 1500 hours, spot testing was performed with 98% sulfuric acid for 72 hours.

**System:** Two coats 74 Series @ 8 mils DFT per coat applied to SSPC-SP6 Commercial Blast prepared steel. Cured 24 hours at 21°C (70°F).

**Result:** No softening or cracking of the film (some discoloration was observed).

### Charter Coating Services Ltd. July 2011

**Method:** NACE TM0185 – Evaluation of Internal Plastic Coatings for Corrosion Control of Tubular Goods by Autoclave Testing.

#### Test Conditions:

Temperature: 45°C/ 203°F

Pressure: 1800 psi

Gas Phase: 5% H<sub>2</sub>S, 5% CO<sub>2</sub>, 90% CH<sub>4</sub>

Organic Phase: Toluene: Xylene 1:1 ratio

Aqueous Phase: 5% NaCl

Duration: Cycle 1 - 96 hours/ Cycle 2 – additional 48 hours (rapid depressurization)

**System:** Two coats 74 Series @ 5-8 mils DFT per coat applied to SSPC-SP 5 White Metal Blast prepared steel.

#### Cycle 1 Results:

Blistering – the test panel remained free of blisters in all three phases

Adhesion – The maintained an A rating in all three phases

Depressurization – no effect from 1500psi to atmospheric over duration of 120 minutes

Cycle 2 Results: (Additional 48 Hours Test with Rapid Decompression from 1800psi to atmospheric in 5 Minutes at 95°C/203°F)

Blistering – The coating showed reactions to the rapid decompression condition as indicated by minor blistering (D#6), the blisters did not extend to substrate. No holidays were detected.

Adhesion – The coating maintained excellent adhesion (rating A) after exposure.

## Safety Information

- Use normal precautions such as gloves, facemasks and barrier creams.
- Adequate ventilation must be maintained. In confined areas, applicators must wear constant flow airline respirators.
- If product comes into contact with skin, wash thoroughly with lukewarm water or diluted Boric Acid, and obtain immediate medical attention.
- This product contains FLAMMABLE materials. Keep away from sparks and open flames. Observe NO SMOKING regulations.
- All electrical equipment and installations should conform to NEC regulations. In areas where explosion hazards exist, applicators should be required to use nonferrous tools, and to wear conductive, non sparking shoes.
- Observe low flash regulations.
- Refer to Safety Data Sheet (SDS) for complete safety instruction

The technical data listed herein has been compiled for your convenience and guidelines are based upon our experience and knowledge. However, since we have no control over the use of this information or this product, no warranty expressed or implied is intended or given. Highland assumes no responsibility whatsoever for coverage, performance or any other damage, including injuries from use of this information or products recommended herein.